

product data sheet

Sasolwax M3B

Code 1388 Revision 4 31 May 2018

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	58 - 64	62
Penetration at 25°C	ASTM D1321	0.1 mm	17 - 23	20
Oil Content	ASTM D721	mass %	4.2 max	3.8
Colour	Sasol 2000	Saybolt	+ 17min	+27
Appearance	Sasol 1074	-	Clear at 90°C	Clear
Water crackle test	Sasol 1087	-	Pass splutter test	Pass
Centrifuge test	Sasol 1052	-	Free from foreign material	Pass

Packaging

Sasolwax M3B is supplied as Liquid, pastilles or powder in 20kg polyethylenen bags or in boxes as 25kg slabs.

Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C

Notice This product information is indicative and does not include any guarantee